WELDER REQUALIFICATION BY RADIOGRAPHIC EXAMINATION

Redacted				Date 4-6-11			
Welder				S.S. No Redacted			
Pipe Dia.	Pipe S	pec. 5L	Gra	de_B	Wall Thic	kness_ • 375_	
Radiographer_	Valley	Indu	strial	X-Ro	·y		
Specific Locati	on <u>Norr</u>	IS ST	Bak	ers fiel	Ó BY	n * 30603916	
Test Inspector	Rec	lacted					
TYPE OF RADIOGRAPHIC INSPECT				V			
Gamn	na Ray	Exposure T	ime <u></u> /v	in	_ Material Sour	ce <u>TR-192</u>	
X-Ray		Voltage	oltage Exposure Time			e	
						ordance with Section the areas set forth Remarks	
	O'clock	O'clock	O'clock				
W-7	6K	0K	ok	X		OK	
EXX10 EXX18 Welder Passed Failed Micro Wire Other Other WELD DEFECTS ABBR: BT = burn Through HL - High Low SI = Slag Inclusion UC = Under Cut P = Porosity IP = Incomplete Penetration						D-27-10	
HL - High Low WT = Wagon Tracks		IF = Incomplete Fusion			C = Crack		